

TEST REPORT

Report No. : GR:TX:1410001801

DATE : 13/01/2010

CHEMICAL ANALYSIS (%)

S.No	Elements	Test Method	Observation (%)
1	Alumina as Al ₂ O ₃	IS 1706(P-3):92 Equi.in principle IS:2000(P3):1985	69.31
2	Iron as Fe ₂ O ₃	IS:2000(PART4):1985(Reaff.2006)	3.58
3	Loss of Ignition(LOI)	IS 2000:PART1:1985(Reaff.2006)	21.38
4	Manganese as MnO	ASTM E 314:2000	Less than 0.01 (DL:0.01%)
5	Phosphorus as P	ASTM C 114:2007	0.06
6	Silica as SiO ₂	IS 2000(PART2):1985(Reaff.2006)	1.26
7	Sulphur as S	ASTM C114:2005&IS2317:1975(Re.04)	0.018
8	Titanium as TiO ₂	IS 2000(PART5):1985(Reaff.2006)	3.74

Note: Observation pertains only to the samples tested, not to its replicates or its batch.
Above Test has been subcontracted to Multilab,SGS,Porbandar.

**** End of Report ****

Per Pro SGS India Private Ltd	
Checked By	Approved By

This is computer generated report, hence signature is not available

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.htm and for electronic format documents, subject to terms and conditions for electronic documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. This document cannot be reproduced except in full, without prior approval of the Company.